

APPROVAL SHEET

MULTILAYER CERAMIC CAPACITORS

General Purpose Series (10V to 100V)

0402 to 1812 Sizes

NP0, X7R & Y5V Dielectrics

RoHS Compliance

*Contents in this sheet are subject to change without prior notice.

1. DESCRIPTION

MLCC consists of a conducting material and electrodes. To manufacture a chip-type SMT and achieve miniaturization, high density and high efficiency, ceramic condensers are used.

WTC's MLCC is made by NP0, X7R and Y5V dielectric material and which provides product with high electrical precision, stability and reliability.

2. FEATURES

- a. A wide selection of sizes is available (0402 to 1812).
- b. High capacitance in given case size.
- c. Capacitor with lead-free termination (pure Tin).

3. APPLICATIONS

- a. For general digital circuit.
- b. For power supply bypass capacitors.
- c. For consumer electronics.
- d. For telecommunication.

4. HOW TO ORDER

<u>1206</u>	<u>E</u>	<u>104</u>	<u>Z</u>	<u>500</u>	<u>C</u>	<u>I</u>
<u>Size</u>	<u>Dielectric</u>	<u>Capacitance</u>	<u>Tolerance</u>	<u>Rated voltage</u>	<u>Termination</u>	<u>Packaging style</u>
Inch (mm) 0402 (1005)	N=NP0 (C0G)	Two significant digits followed by no. of zeros. And R is in place of decimal point.	B=±0.1pF C=±0.25pF	Two significant digits followed by no. of zeros. And R is in place of decimal point.	C=Cu/Ni/Sn (for NP0, X7R, Y5V dielectric) L=Ag/Ni/Sn (for partial NP0 items)	T=7" reeled R=7" reeled (2mm pitch for 0603 size; paper tape) G=13" reeled
0603 (1608)	B=X7R		D=±0.5pF			
0805 (2012)	F=Y5V		F=±1%			
1206 (3216)			G=±2%			
1210 (3225)			J=±5%	100=10 VDC		
1812 (4532)		eg.: 0R5=0.5pF 1R0=1.0pF 104=10x10 ⁴ =100nF	K=±10% M=±20% Z=−20/+80%	160=16 VDC 250=25 VDC 500=50 VDC 101=100 VDC		

* Partial NP0 items are with Ag/Ni/Sn terminations, please ref to below product range of NPO dielectric for detail.

5. EXTERNAL DIMENSIONS

<u>Size</u> <u>Inch (mm)</u>	<u>L (mm)</u>	<u>W (mm)</u>	<u>T (mm)/Symbol</u>	<u>Remark</u>	<u>M_B (mm)</u>
0402 (1005)	1.00±0.05	0.50±0.05	0.50±0.05	N #	0.25 +0.05/-0.10
0603 (1608)	1.60±0.10	0.80±0.10	0.80±0.07	S	0.40±0.15
	1.60 +0.15/-0.10	0.80 +0.15/-0.10	0.80 +0.15/-0.10	X	
0805 (2012)	2.00±0.15	1.25±0.10	0.60±0.10	A	0.50±0.20
			0.80±0.10	B	
			1.25±0.10	D #	
			1.25±0.20	I #	
1206 (3216)	3.20±0.15	1.60±0.15	0.80±0.10	B	0.60±0.20
			0.95±0.10	C	
			1.15±0.15	J #	
			1.25±0.10	D #	
	3.20±0.20	1.60±0.20	1.60±0.20	G #	0.75±0.25
1210 (3225)	3.20±0.30	2.50±0.20	1.60±0.30/-0.10	P #	
			0.95±0.10	C #	
			1.25±0.10	D #	
	3.20±0.40	2.50±0.30	1.60±0.20	G #	
			2.00±0.20	K #	
1812 (4532)	4.50±0.40	3.20±0.30	1.25±0.10	D #	0.75±0.25
			2.00±0.20	K #	

Reflow soldering only is recommended.




Fig. 1 The outline of MLCC

6. GENERAL ELECTRICAL DATA

Dielectric	NP0	X7R	Y5V	
Size	0402, 0603, 0805, 1206, 1210, 1812			
Capacitance range*	0.5pF to 0.039μF	100pF to 0.82μF	10nF to 0.68μF	
Capacitance tolerance**	Cap≤5pF: B ($\pm 0.1\mu F$), C ($\pm 0.25\mu F$) 5pF<Cap<10pF: C ($\pm 0.25\mu F$), D ($\pm 0.5\mu F$) Cap≥10pF: F ($\pm 1\%$), G ($\pm 2\%$), J ($\pm 5\%$), K ($\pm 10\%$)	J ($\pm 5\%$), K ($\pm 10\%$), M ($\pm 20\%$)	M ($\pm 20\%$), Z (-20/+80%)	
Rated voltage (WVDC)	10V, 16V, 25V, 50V, 100V	6.3V, 10V, 16V, 25V, 50V, 100V		
Tan δ*	Cap<30pF: Q≥400+20C Cap≥30pF: Q≥1000	Note 1		
Insulation resistance at Ur	$\geq 10G\Omega$ or $RxC \geq 500\Omega \cdot F$ whichever is less			
Operating temperature	-55 to +125°C			
Capacitance characteristic	±30ppm	±15%	+30/-80%	
Termination	Ni/Sn (lead-free termination)			

* Measured at the condition of 30~70% related humidity.

NP0: Apply $1.0 \pm 0.2\text{VRms}$, $1.0\text{MHz} \pm 10\%$ for $\text{Cap} \leq 1000\text{pF}$ and $1.0 \pm 0.2\text{VRms}$, $1.0\text{kHz} \pm 10\%$ for $\text{Cap} > 1000\text{pF}$, 25°C at ambient temperature

X7R: Apply $1.0 \pm 0.2\text{VRms}$, $1.0\text{kHz} \pm 10\%$, at 25°C ambient temperature.

Y5V: Apply $1.0 \pm 0.2\text{VRms}$, $1.0\text{kHz} \pm 10\%$, at 20°C ambient temperature.

** Preconditioning for Class II MLCC: Perform a heat treatment at $150 \pm 10^\circ\text{C}$ for 1 hour, then leave in a mbient condition for 24 ± 2 hours before measurement.

Note 1:

X7R/X5R

Rated vol.	D.F. ≤	Exception of D.F. ≤
≥50V	2.5%	3% 0603≥0.047μF; 0805≥0.18μF; 1206≥0.47μF
25V	3.5%	5% 0805≥1μF; 1210≥10μF
		7% 0603≥0.33μF; 1206≥4.7μF
		10% 0402≥0.10μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥6.8μF
		5% 0402≥0.033μF; 0603≥0.15μF; 0805≥0.68μF; 1206≥2.2μF; 1210≥4.7μF
16V	3.5%	10% 0603≥0.68μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF
		15% 0402≥0.33μF; 0603≥0.33μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥22μF;
		15% 0201≥0.1μF; 0402≥1μF
10V	5%	15% 0603≥10μF; 0805≥4.7μF; 1206≥47μF; 1210≥100μF;
		20% 0402≥2.2μF

Y5V

Rated vol.	D.F. ≤	Exception of D.F. ≤
≥50V	5%	7% 0603≥0.1μF; 0805≥0.47μF; 1206≥4.7μF
35V	7%	--- ---
		7% 0402≥0.047μF; 0603≥0.1μF; 0805≥0.33μF; 1206≥1μF; 1210≥4.7μF
25V	5%	9% 0402≥0.068μF; 0603≥0.47μF; 1206≥4.7μF; 1210≥22μF
		7% 0402≥0.22μF
16V (C<1.0μF)	7%	9% 0603≥2.2μF; 0805≥3.3μF; 1206≥10μF; 1210≥22μF; 1812≥47μF
16V (C≥1.0μF)	9%	12.5% 0402≥0.47μF
10V	12.5%	20% 0402≥0.47μF
6.3V	20%	--- ---

7. CAPACITANCE RANGE (NP0 Dielectric)

7-1 0402, 0603, 0805 Sizes

DIELECTRIC		NP0														
SIZE		0402					0603					0805				
RATED VOLTAGE		10	16	25	50	100	10	16	25	50	100	10	16	25	50	100
Capacitance	0.1pF (0R1)	N	N	N	N											
	0.2pF (0R2)	N	N	N	N											
	0.3pF (0R3)	N	N	N	N											
	0.4pF (0R4)	N	N	N	N											
	0.5pF (0R5)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	0.6pF (0R6)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	0.7pF (0R7)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	0.8pF (0R8)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	0.9pF (0R9)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	1.0pF (1R0)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	1.2pF (1R2)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	1.5pF (1R5)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	1.8pF (1R8)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	2.2pF (2R2)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	2.7pF (2R7)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	3.3pF (3R3)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	3.9pF (3R9)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	4.7pF (4R7)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	5.6pF (5R6)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	6.8pF (6R8)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	8.2pF (8R2)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	10pF (100)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	12pF (120)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	15pF (150)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	18pF (180)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	22pF (220)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	27pF (270)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	33pF (330)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	39pF (390)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	47pF (470)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	56pF (560)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	68pF (680)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	82pF (820)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	100pF (101)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	120pF (121)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	150pF (151)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	180pF (181)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	220pF (221)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	270pF (271)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	330pF (331)	N	N	N	N	N	S	S	S	S	S	A	A	A	A	
	390pF (391)	N	N	N	N	N	S	S	S	S	S	B	B	B	B	
	470pF (471)	N	N	N	N	N	S	S	S	S	S	B	B	B	B	
	560pF (561)	N	N	N	N	N	S	S	S	S	S	B	B	B	B	
	680pF (681)	N	N	N	N	N	S	S	S	S	S	B	B	B	B	
	820pF (821)	N	N	N	N	N	S	S	S	S	S	B	B	B	B	
	1,000pF (102)	N	N	N	N	N	S	S	S	S	S	B	B	B	B	
	1,200pF (122)						X	X	X	X		B	B	B	B	
	1,500pF (152)						X	X	X	X		B	B	B	B	
	1,800pF (182)						X	X	X	X		B	B	B	B	
	2,200pF (222)						X	X	X	X		B	B	B	B	
	2,700pF (272)						X	X	X	X		D	D	D	D	
	3,300pF (332)						X	X	X	X		D	D	D	D	
	3,900pF (392)											D	D	D	D	
	4,700pF (472)											D	D	D	D	
	5,600pF (562)											D	D	D	D	
	6,800pF (682)											D	D	D	D	
	8,200pF (822)											D	D	D	D	
	0.010uF (103)											D	D	D	D	
	0.012uF (123)											D^	D^			

- The letter in cell is expressed the symbol of product thickness.
- The letter in cell with “^” mark is expressed product with Ag/Ni/Sn terminations.
- For more information about products with special capacitance or other data, please contact WTC local representative.

7-2 1206, 1210, 1812 Sizes

DIELECTRIC SIZE		NP0												
RATED VOLTAGE		10	16	25	50	100	10	16	25	50	100	16	50	100
Capacitance	1.0pF (1R0)													
	1.2pF (1R2)	B	B	B	B	B								
	1.5pF (1R5)	B	B	B	B	B								
	1.8pF (1R8)	B	B	B	B	B								
	2.2pF (2R2)	B	B	B	B	B								
	2.7pF (2R7)	B	B	B	B	B								
	3.3pF (3R3)	B	B	B	B	B								
	3.9pF (3R9)	B	B	B	B	B								
	4.7pF (4R7)	B	B	B	B	B								
	5.6pF (5R6)	B	B	B	B	B								
	6.8pF (6R8)	B	B	B	B	B								
	8.2pF (8R2)	B	B	B	B	B								
	10pF (100)	B	B	B	B	B	C	C	C	C	C	D	D	D
	12pF (120)	B	B	B	B	B	C	C	C	C	C	D	D	D
	15pF (150)	B	B	B	B	B	C	C	C	C	C	D	D	D
	18pF (180)	B	B	B	B	B	C	C	C	C	C	D	D	D
	22pF (220)	B	B	B	B	B	C	C	C	C	C	D	D	D
	27pF (270)	B	B	B	B	B	C	C	C	C	C	D	D	D
	33pF (330)	B	B	B	B	B	C	C	C	C	C	D	D	D
	39pF (390)	B	B	B	B	B	C	C	C	C	C	D	D	D
	47pF (470)	B	B	B	B	B	C	C	C	C	C	D	D	D
	56pF (560)	B	B	B	B	B	C	C	C	C	C	D	D	D
	68pF (680)	B	B	B	B	B	C	C	C	C	C	D	D	D
	82pF (820)	B	B	B	B	B	C	C	C	C	C	D	D	D
	100pF (101)	B	B	B	B	B	C	C	C	C	C	D	D	D
	120pF (121)	B	B	B	B	B	C	C	C	C	C	D	D	D
	150pF (151)	B	B	B	B	B	C	C	C	C	C	D	D	D
	180pF (181)	B	B	B	B	B	C	C	C	C	C	D	D	D
	220pF (221)	B	B	B	B	B	C	C	C	C	C	D	D	D
	270pF (271)	B	B	B	B	B	C	C	C	C	C	D	D	D
	330pF (331)	B	B	B	B	B	C	C	C	C	C	D	D	D
	390pF (391)	B	B	B	B	B	C	C	C	C	C	D	D	D
	470pF (471)	B	B	B	B	B	C	C	C	C	C	D	D	D
	560pF (561)	B	B	B	B	B	C	C	C	C	C	D	D	D
	680pF (681)	B	B	B	B	B	C	C	C	C	C	D	D	D
	820pF (821)	B	B	B	B	B	C	C	C	C	C	D	D	D
	1,000pF (102)	B	B	B	B	B	C	C	C	C	C	D	D	D
	1,200pF (122)	B	B	B	B	B	C	C	C	C	C	D	D	D
	1,500pF (152)	B	B	B	B	B	C	C	C	C	C	D	D	D
	1,800pF (182)	B	B	B	B	B	C	C	C	C	C	D	D	D
	2,200pF (222)	B	B	B	B	B	C	C	C	C	C	D	D	D
	2,700pF (272)	B	B	B	B	B	C	C	C	C	C	D	D	D
	3,300pF (332)	B	B	B	B	B	C	C	C	C	C	D	D	D
	3,900pF (392)	B	B	B	B	B	C	C	C	C	C	D	D	D
	4,700pF (472)	B	B	B	B	B	C	C	C	C	C	D	D	D
	5,600pF (562)	B	B	B	B	B	C	C	C	C	C	D	D	D
	6,800pF (682)	C	C	C	C	C	C	C	C	C	C	D	D	D
	8,200pF (822)	D	D	D	D	D	C	C	C	C	C	D	D	D
	0.010μF (103)	D	D	D	D	D	C	C	C	C	C	D	D	D
	0.012μF (123)	D^	D^				C	C	D	D	D	D	D	D
	0.015μF (153)	D^	D^				C	C	D	D	D	D	D	D
	0.018μF (183)	D^	D^									D	D	D
	0.022μF (223)	D^	D^									D	D	D
	0.027μF (273)	D^	D^									D	D	D
	0.033μF (333)	D^	D^									D	D	D
	0.039μF (393)	G^	G^											

- The letter in cell is expressed the symbol of product thickness.
- The letter in cell with “^” mark is expressed product with Ag/Ni/Sn terminations.
- For more information about products with special capacitance or other data, please contact WTC local representative.

8. CAPACITANCE RANGE (X7R Dielectric)

8-1 0402, 0603, 0805 Sizes

DIELECTRIC		X7R													
SIZE		0402				0603					0805				
RATED VOLTAGE (VDC)		10	16	25	50	10	16	25	50	100	10	16	25	50	100
Capacitance	100pF (101)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	120pF (121)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	150pF (151)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	180pF (181)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	220pF (221)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	270pF (271)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	330pF (331)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	390pF (391)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	470pF (471)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	560pF (561)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	680pF (681)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	820pF (821)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	1,000pF (102)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	1,200pF (122)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	1,500pF (152)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	1,800pF (182)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	2,200pF (222)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	2,700pF (272)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	3,300pF (332)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	3,900pF (392)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	4,700pF (472)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	5,600pF (562)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	6,800pF (682)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	8,200pF (822)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	0.010μF (103)	N	N	N	N	S	S	S	S	S	B	B	B	B	B
	0.012μF (123)	N	N	N		S	S	S	S		B	B	B	B	B
	0.015μF (153)	N	N	N		S	S	S	S		B	B	B	B	B
	0.018μF (183)	N	N	N		S	S	S	S		B	B	B	B	B
	0.022μF (223)	N	N	N		S	S	S	S		B	B	B	B	B
	0.027μF (273)	N	N	N		S	S	S	S		B	B	B	B	D
	0.033μF (333)	N	N	N		S	S	S	X		B	B	B	B	D
	0.039μF (393)	N	N	N		S	S	S	X		B	B	B	B	D
	0.047μF (473)	N	N	N		S	S	S	X		B	B	B	B	D
	0.056μF (563)	N	N			S	S	S	X		B	B	B	B	D
	0.068μF (683)	N	N			S	S	S	X		B	B	B	B	D
	0.082μF (823)	N	N			S	S	S	X		B	B	B	B	D
	0.10μF (104)	N	N			S	S	S	X		B	B	B	B	D
	0.12μF (124)					S	S	X			B	B	B	D	
	0.15μF (154)					S	S	X			D	D	D	D	
	0.18μF (184)					S	S	X			D	D	D	D	
	0.22μF (224)					S	S	X			D	D	D	D	
	0.27μF (274)					X	X	X			D	D	D	D	I
	0.33μF (334)					X	X	X			D	D	D	D	I
	0.39μF (394)					X	X	X			D	D	D	D	I
	0.47μF (474)					X	X	X			D	D	D	D	I
	0.56μF (564)										D	D	D	D	
	0.68μF (684)										D	D	D	D	
	0.82μF (824)										D	D	D	D	

1. The letter in cell is expressed the symbol of product thickness.

2. For more information about products with special capacitance or other data, please contact WTC local representative.

8-2 1206, 1210, 1812 Sizes

DIELECTRIC		X7R														
SIZE		1206					1210				1812					
RATED VOLTAGE		10	16	25	50	100	10	16	25	50	100	10	16	25	50	100
Capacitance	100pF (101)															
	120pF (121)															
	150pF (151)	B	B	B	B	B										
	180pF (181)	B	B	B	B	B										
	220pF (221)	B	B	B	B	B										
	270pF (271)	B	B	B	B	B										
	330pF (331)	B	B	B	B	B										
	390pF (391)	B	B	B	B	B										
	470pF (471)	B	B	B	B	B										
	560pF (561)	B	B	B	B	B										
	680pF (681)	B	B	B	B	B										
	820pF (821)	B	B	B	B	B										
	1,000pF (102)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	1,200pF (122)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	1,500pF (152)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	1,800pF (182)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	2,200pF (222)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	2,700pF (272)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	3,300pF (332)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	3,900pF (392)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	4,700pF (472)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	5,600pF (562)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	6,800pF (682)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	8,200pF (822)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	0.010μF (103)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	0.012μF (123)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	0.015μF (153)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	0.018μF (183)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	0.022μF (223)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	0.027μF (273)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	0.033μF (333)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	0.039μF (393)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	0.047μF (473)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	0.056μF (563)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	0.068μF (683)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	D
	0.082μF (823)	B	B	B	B	D	C	C	C	C	C	D	D	D	D	D
	0.10μF (104)	B	B	B	B	D	C	C	C	C	C	D	D	D	D	D
	0.12μF (124)	B	B	B	B	D	C	C	C	C	C	D	D	D	D	D
	0.15μF (154)	C	C	C	C	G	C	C	C	C	D	D	D	D	D	D
	0.18μF (184)	C	C	C	C	G	C	C	C	C	D	D	D	D	D	D
	0.22μF (224)	C	C	C	C	G	C	C	C	C	D	D	D	D	D	D
	0.27μF (274)	C	C	C	D	G	C	C	C	C	G	D	D	D	D	D
	0.33μF (334)	C	C	C	D	G	C	C	C	D	G	D	D	D	D	D
	0.39μF (394)	C	C	J	P	G	C	C	C	D	M	D	D	D	D	D
	0.47μF (474)	J	J	J	P	G	C	C	C	D	M	D	D	D	D	K
	0.56μF (564)	J	J	J	P	P	D	D	D	D	M	D	D	D	D	K
	0.68μF (684)	J	J	J	P	P	D	D	D	D	K	D	D	D	K	K
	0.82μF (824)	J	J	J	P	P	D	D	D	D	K	D	D	D	K	K

1. The letter in cell is expressed the symbol of product thickness.

2. For more information about products with special capacitance or other data, please contact WTC local representative.

9. CAPACITANCE RANGE (Y5V Dielectric)

9-1 0402, 0603, 0805 Sizes

DIELECTRIC		Y5V													
SIZE		0402					0603				0805				
RATED VOLTAGE		6.3	10	16	25	50	10	16	25	50	10	16	25	50	100
Capacitance	0.010μF (103)		N	N	N	N	S	S	S	S	A	A	A	A	B
	0.015μF (153)		N	N	N	N	S	S	S	S	A	A	A	A	B
	0.022μF (223)		N	N	N	N	S	S	S	S	A	A	A	A	B
	0.033μF (333)		N	N	N	N	S	S	S	S	A	A	A	A	B
	0.047μF (473)		N	N	N		S	S	S	S	A	A	A	A	B
	0.068μF (683)		N	N	N		S	S	S	S	A	A	A	A	B
	0.10μF (104)		N	N	N		S	S	S	S	A	A	A	A	B
	0.15μF (154)		N	N			S	S	S	S	A	A	A	A	
	0.22μF (224)	N	N	N	N		S	S	S	S	A	A	A	A	
	0.33μF (334)	N	N	N			S	S	S		B	B	B	B	
	0.47μF (474)	N	N	N			S	S	X	S	B	B	B	B	
	0.68μF (684)	N					S	X			B	B	D	D	

9-2 1206, 1210, 1812 Sizes

DIELECTRIC		Y5V														
SIZE		1206					1210					1812				
RATED VOLTAGE		10	16	25	50	100	10	16	25	50	100	10	16	25	50	100
Capacitance	0.010μF (103)	B	B	B	B	B					C				D	
	0.015μF (153)	B	B	B	B	B					C				D	
	0.022μF (223)	B	B	B	B	B					C				D	
	0.033μF (333)	B	B	B	B	B					C				D	
	0.047μF (473)	B	B	B	B	B					C				D	
	0.068μF (683)	B	B	B	B	B					C				D	
	0.10μF (104)	B	B	B	B	B	C	C	C	C	C	D	D	D	D	
	0.15μF (154)	B	B	B	B	C	C	C	C	C	C	D	D	D	D	
	0.22μF (224)	B	B	B	B	C	C	C	C	C	C	D	D	D	D	
	0.33μF (334)	B	B	B	B		C	C	C	C	C	D	D	D	D	
	0.47μF (474)	B	B	B	B		C	C	C	C		D	D	D	D	
	0.68μF (684)	B	B	B	B		C	C	C	C		D	D	D	D	

1. The letter in cell is expressed the symbol of product thickness.

2. For more information about products with special capacitance or other data, please contact WTC local representative.

10. PACKAGING STYLE AND QUANTITY

Size	Thickness (mm)/Symbol	Paper tape				Plastic tape			
		7" reel	13" reel	7" reel	13" reel	7" reel	13" reel	7" reel	13" reel
0402 (1005)	0.50±0.05	N	10k	50k		-		-	-
0603 (1608)	0.80±0.07	S	4k	15k		-		-	-
	0.80+0.15/-0.10	X	4k	15k		-		-	-
	0.60±0.10	A	4k	15k		-		-	-
0805 (2012)	0.80±0.10	B	4k	15k		-		-	-
	1.25±0.10	D	-	-		3k		10k	
	1.25±0.20	I	-	-		3k		10k	
	0.80±0.10	B	4k	15k		-		-	-
1206 (3216)	0.95±0.10	C	-	-		3k		10k	
	1.15±0.15	J	-	-		3k		10k	
	1.25±0.10	D	-	-		3k		10k	
	1.60±0.20	G	-	-		2k		10k	
	1.60+0.30/-0.10	P	-	-		2k		9k	
1210 (3225)	0.95±0.10	C	-	-		3k		10k	
	1.25±0.10	D	-	-		3k		10k	
	1.60±0.20	G	-	-		2k		-	
	2.00±0.20	K	-	-		1k		6k	
	2.50±0.30	M	-	-		1k		-	
1812 (4532)	1.25±0.10	D	-	-		1k		-	
	2.00±0.20	K	-	-		1k		-	

Unit: pieces

11. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements																																																																																																														
1.	Visual and Mechanical	---	* No remarkable defect. * Dimensions to conform to individual specification sheet.																																																																																																														
2.	Capacitance	Class I:NPO	* Shall not exceed the limits given in the detailed spec.																																																																																																														
3.	Q/D.F. (Dissipation Factor)	Cap \leq 1000pF 1.0 \pm 0.2Vrms, 1MHz \pm 10% Cap>1000pF 1.0 \pm 0.2Vrms, 1KHz \pm 10% Class II:X7R, X5R, Y5V Cap \leq 10μF, 1.0 \pm 0.2Vrms, 1kHz \pm 10% Cap>10μF, 0.5 \pm 0.2Vrms, 120Hz \pm 20%	NP0: Cap \geq 30pF, Q \geq 1000; Cap<30pF, Q \geq 400+20C X7R, X5R: <table border="1"> <thead> <tr> <th>Rated Vol.</th> <th>D.F. \leq</th> <th colspan="3">Exception of D.F. \leq</th> </tr> </thead> <tbody> <tr> <td>\geq 50V</td> <td>2.5%</td> <td>3%</td> <td>0603\geq 0.047μF; 0805\geq 0.18μF; 1206\geq 0.47μF</td> <td></td> </tr> <tr> <td></td> <td></td> <td>5%</td> <td>0805\geq 1μF; 1210\geq 10μF</td> <td></td> </tr> <tr> <td>25V</td> <td>3.5%</td> <td>7%</td> <td>0603\geq 0.33μF; 1206\geq 4.7μF</td> <td></td> </tr> <tr> <td></td> <td></td> <td>10%</td> <td>0402\geq 0.10μF; 0603\geq 0.47μF; 0805\geq 2.2μF; 1206\geq 6.8μF</td> <td></td> </tr> <tr> <td>16V</td> <td>3.5%</td> <td>5%</td> <td>0402\geq 0.033μF; 0603\geq 0.15μF; 0805\geq 0.68μF; 1206\geq 2.2μF; 1210\geq 4.7μF</td> <td></td> </tr> <tr> <td></td> <td></td> <td>10%</td> <td>0603\geq 0.68μF; 0805\geq 2.2μF; 1206\geq 4.7μF; 1210\geq 22μF</td> <td></td> </tr> <tr> <td>10V</td> <td>5%</td> <td>10%</td> <td>0402\geq 0.33μF; 0603\geq 0.33μF; 0805\geq 2.2μF; 1206\geq 2.2μF; 1210\geq 22μF</td> <td></td> </tr> <tr> <td></td> <td></td> <td>15%</td> <td>0201\geq 0.1μF; 0402\geq 1μF</td> <td></td> </tr> <tr> <td>6.3V</td> <td>10%</td> <td>15%</td> <td>0603\geq 10μF; 0805\geq 4.7μF; 1206\geq 47μF; 1210\geq 100μF;</td> <td></td> </tr> <tr> <td></td> <td></td> <td>20%</td> <td>0402\geq 2.2μF</td> <td></td> </tr> </tbody> </table> Y5V: <table border="1"> <thead> <tr> <th>Rated vol.</th> <th>D.F. \leq</th> <th colspan="3">Exception of D.F. \leq</th> </tr> </thead> <tbody> <tr> <td>\geq 50V</td> <td>5%</td> <td>7%</td> <td>0603\geq 0.1μF; 0805\geq 0.47μF; 1206\geq 4.7μF</td> <td></td> </tr> <tr> <td>35V</td> <td>7%</td> <td>---</td> <td>---</td> <td></td> </tr> <tr> <td>25V</td> <td>5%</td> <td>7%</td> <td>0402\geq 0.047μF; 0603\geq 0.1μF; 0805\geq 0.33μF; 1206\geq 1μF; 1210\geq 4.7μF</td> <td></td> </tr> <tr> <td></td> <td></td> <td>9%</td> <td>0402\geq 0.068μF; 0603\geq 0.47μF; 1206\geq 4.7μF; 1210\geq 22μF</td> <td></td> </tr> <tr> <td>16V</td> <td>7%</td> <td>9%</td> <td>0402\geq 0.068μF; 0603\geq 0.68μF</td> <td></td> </tr> <tr> <td>(C<1.0μF)</td> <td></td> <td>12.5%</td> <td>0402\geq 0.22μF</td> <td></td> </tr> <tr> <td>16V</td> <td>9%</td> <td>12.5%</td> <td>0603\geq 2.2μF; 0805\geq 3.3μF; 1206\geq 10μF; 1210\geq 22μF; 1812\geq 47μF</td> <td></td> </tr> <tr> <td>(C\geq1.0μF)</td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>10V</td> <td>12.5%</td> <td>20%</td> <td>0402\geq 0.47μF</td> <td></td> </tr> <tr> <td>6.3V</td> <td>20%</td> <td>---</td> <td>---</td> <td></td> </tr> </tbody> </table>	Rated Vol.	D.F. \leq	Exception of D.F. \leq			\geq 50V	2.5%	3%	0603 \geq 0.047μF; 0805 \geq 0.18μF; 1206 \geq 0.47μF				5%	0805 \geq 1μF; 1210 \geq 10μF		25V	3.5%	7%	0603 \geq 0.33μF; 1206 \geq 4.7μF				10%	0402 \geq 0.10μF; 0603 \geq 0.47μF; 0805 \geq 2.2μF; 1206 \geq 6.8μF		16V	3.5%	5%	0402 \geq 0.033μF; 0603 \geq 0.15μF; 0805 \geq 0.68μF; 1206 \geq 2.2μF; 1210 \geq 4.7μF				10%	0603 \geq 0.68μF; 0805 \geq 2.2μF; 1206 \geq 4.7μF; 1210 \geq 22μF		10V	5%	10%	0402 \geq 0.33μF; 0603 \geq 0.33μF; 0805 \geq 2.2μF; 1206 \geq 2.2μF; 1210 \geq 22μF				15%	0201 \geq 0.1μF; 0402 \geq 1μF		6.3V	10%	15%	0603 \geq 10μF; 0805 \geq 4.7μF; 1206 \geq 47μF; 1210 \geq 100μF;				20%	0402 \geq 2.2μF		Rated vol.	D.F. \leq	Exception of D.F. \leq			\geq 50V	5%	7%	0603 \geq 0.1μF; 0805 \geq 0.47μF; 1206 \geq 4.7μF		35V	7%	---	---		25V	5%	7%	0402 \geq 0.047μF; 0603 \geq 0.1μF; 0805 \geq 0.33μF; 1206 \geq 1μF; 1210 \geq 4.7μF				9%	0402 \geq 0.068μF; 0603 \geq 0.47μF; 1206 \geq 4.7μF; 1210 \geq 22μF		16V	7%	9%	0402 \geq 0.068μF; 0603 \geq 0.68μF		(C<1.0μF)		12.5%	0402 \geq 0.22μF		16V	9%	12.5%	0603 \geq 2.2μF; 0805 \geq 3.3μF; 1206 \geq 10μF; 1210 \geq 22μF; 1812 \geq 47μF		(C \geq 1.0μF)					10V	12.5%	20%	0402 \geq 0.47μF		6.3V	20%	---	---	
Rated Vol.	D.F. \leq	Exception of D.F. \leq																																																																																																															
\geq 50V	2.5%	3%	0603 \geq 0.047μF; 0805 \geq 0.18μF; 1206 \geq 0.47μF																																																																																																														
		5%	0805 \geq 1μF; 1210 \geq 10μF																																																																																																														
25V	3.5%	7%	0603 \geq 0.33μF; 1206 \geq 4.7μF																																																																																																														
		10%	0402 \geq 0.10μF; 0603 \geq 0.47μF; 0805 \geq 2.2μF; 1206 \geq 6.8μF																																																																																																														
16V	3.5%	5%	0402 \geq 0.033μF; 0603 \geq 0.15μF; 0805 \geq 0.68μF; 1206 \geq 2.2μF; 1210 \geq 4.7μF																																																																																																														
		10%	0603 \geq 0.68μF; 0805 \geq 2.2μF; 1206 \geq 4.7μF; 1210 \geq 22μF																																																																																																														
10V	5%	10%	0402 \geq 0.33μF; 0603 \geq 0.33μF; 0805 \geq 2.2μF; 1206 \geq 2.2μF; 1210 \geq 22μF																																																																																																														
		15%	0201 \geq 0.1μF; 0402 \geq 1μF																																																																																																														
6.3V	10%	15%	0603 \geq 10μF; 0805 \geq 4.7μF; 1206 \geq 47μF; 1210 \geq 100μF;																																																																																																														
		20%	0402 \geq 2.2μF																																																																																																														
Rated vol.	D.F. \leq	Exception of D.F. \leq																																																																																																															
\geq 50V	5%	7%	0603 \geq 0.1μF; 0805 \geq 0.47μF; 1206 \geq 4.7μF																																																																																																														
35V	7%	---	---																																																																																																														
25V	5%	7%	0402 \geq 0.047μF; 0603 \geq 0.1μF; 0805 \geq 0.33μF; 1206 \geq 1μF; 1210 \geq 4.7μF																																																																																																														
		9%	0402 \geq 0.068μF; 0603 \geq 0.47μF; 1206 \geq 4.7μF; 1210 \geq 22μF																																																																																																														
16V	7%	9%	0402 \geq 0.068μF; 0603 \geq 0.68μF																																																																																																														
(C<1.0μF)		12.5%	0402 \geq 0.22μF																																																																																																														
16V	9%	12.5%	0603 \geq 2.2μF; 0805 \geq 3.3μF; 1206 \geq 10μF; 1210 \geq 22μF; 1812 \geq 47μF																																																																																																														
(C \geq 1.0μF)																																																																																																																	
10V	12.5%	20%	0402 \geq 0.47μF																																																																																																														
6.3V	20%	---	---																																																																																																														
4.	Dielectric Strength	* To apply voltage (\leq 100V) 250%. * Duration: 1 to 5 sec. * Charge and discharge current less than 50mA.	* No evidence of damage or flash over during test.																																																																																																														
5.	Insulation Resistance	To apply rated voltage for max. 120 sec.	10GΩ or $RxC \geq 500\Omega\text{-}F$ whichever is smaller. Class II (X7R, X5R, Y5V) <table border="1"> <thead> <tr> <th>Rated voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>100V: X7R</td> <td rowspan="4">10GΩ or $RxC \geq 100 \Omega\text{-}F$ whichever is smaller.</td> </tr> <tr> <td>16V: 0402\geq0.22μF</td> </tr> <tr> <td>10V: 0201\geq47nF; 0402\geq0.47μF; 0603\geq0.47μF; 0805\geq2.2μF; 1206\geq4.7μF; 1210\geq47μF</td> </tr> <tr> <td>6.3V</td> </tr> </tbody> </table>	Rated voltage	Insulation Resistance	100V: X7R	10GΩ or $RxC \geq 100 \Omega\text{-}F$ whichever is smaller.	16V: 0402 \geq 0.22μF	10V: 0201 \geq 47nF; 0402 \geq 0.47μF; 0603 \geq 0.47μF; 0805 \geq 2.2μF; 1206 \geq 4.7μF; 1210 \geq 47μF	6.3V																																																																																																							
Rated voltage	Insulation Resistance																																																																																																																
100V: X7R	10GΩ or $RxC \geq 100 \Omega\text{-}F$ whichever is smaller.																																																																																																																
16V: 0402 \geq 0.22μF																																																																																																																	
10V: 0201 \geq 47nF; 0402 \geq 0.47μF; 0603 \geq 0.47μF; 0805 \geq 2.2μF; 1206 \geq 4.7μF; 1210 \geq 47μF																																																																																																																	
6.3V																																																																																																																	
6.	Temperature Coefficient	With no electrical load.	 <table border="1"> <thead> <tr> <th>T.C.</th> <th>Capacitance Change</th> </tr> </thead> <tbody> <tr> <td>NPO</td> <td>Within $\pm 30\text{ppm}/^{\circ}\text{C}$</td> </tr> <tr> <td>X7R</td> <td>Within $\pm 15\%$</td> </tr> <tr> <td>X5R</td> <td>Within $\pm 15\%$</td> </tr> <tr> <td>Y5V</td> <td>Within $\pm 30\%/-80\%$</td> </tr> </tbody> </table>	T.C.	Capacitance Change	NPO	Within $\pm 30\text{ppm}/^{\circ}\text{C}$	X7R	Within $\pm 15\%$	X5R	Within $\pm 15\%$	Y5V	Within $\pm 30\%/-80\%$																																																																																																				
T.C.	Capacitance Change																																																																																																																
NPO	Within $\pm 30\text{ppm}/^{\circ}\text{C}$																																																																																																																
X7R	Within $\pm 15\%$																																																																																																																
X5R	Within $\pm 15\%$																																																																																																																
Y5V	Within $\pm 30\%/-80\%$																																																																																																																
7.	Adhesive Strength of Termination	* Pressurizing force : 5N (\leq 0603) and 10N ($>$ 0603) * Test time: 10 \pm 1 sec.	* No remarkable damage or removal of the terminations.																																																																																																														

No.	Item	Test Condition	Requirements															
8.	Vibration Resistance	<ul style="list-style-type: none"> * Vibration frequency: 10~55 Hz/min. * Total amplitude: 1.5mm * Test time: 6 hrs. (Two hrs each in three mutually perpendicular directions.) 	<ul style="list-style-type: none"> * No remarkable damage. * Cap change and Q/D.F.: To meet initial spec. 															
9.	Solderability	<ul style="list-style-type: none"> * Solder temperature: 235±5°C * Dipping time: 2±0.5 sec. 	95% min. coverage of all metallized area.															
10.	Bending Test	<ul style="list-style-type: none"> * The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1 mm per second until the deflection becomes 1 mm and then the pressure shall be maintained for 5±1 sec. * Measurement to be made after keeping at room temp. for 24±2 hrs. (Class I) or 48±4 hrs. (Class II). 	<ul style="list-style-type: none"> * No remarkable damage. * Cap change : <ul style="list-style-type: none"> NP0: within ±5% or 0.5pF whichever is larger X7R, X5R: within ±12.5% Y5V: within ±30% (This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test.) 															
11.	Resistance to Soldering Heat	<ul style="list-style-type: none"> * Solder temperature: 260±5°C * Dipping time: 10±1 sec * Preheating: 120 to 150°C for 1 minute before immerse the capacitor in a eutectic solder. * Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 48±4 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs. (Class I) or 48±4 hrs. (Class II). 	<ul style="list-style-type: none"> * No remarkable damage. * Cap change: <ul style="list-style-type: none"> NP0: within ±2.5% or 0.25pF whichever is larger X7R, X5R: within ±7.5% Y5V: within ±20% * Q/D.F., I.R. and dielectric strength: To meet initial requirements. * 25% max. leaching on each edge. 															
12.	Temperature Cycle	<ul style="list-style-type: none"> * Conduct the five cycles according to the temperatures and time. <table border="1" style="margin-left: 10px;"> <thead> <tr> <th>Step</th> <th>Temp. (°C)</th> <th>Time (min.)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Min. operating temp. +0/-3</td> <td>30±3</td> </tr> <tr> <td>2</td> <td>Room temp.</td> <td>2~3</td> </tr> <tr> <td>3</td> <td>Max. operating temp. +3/-0</td> <td>30±3</td> </tr> <tr> <td>4</td> <td>Room temp.</td> <td>2~3</td> </tr> </tbody> </table> <ul style="list-style-type: none"> * Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 48±4 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs. (Class I) or 48±4 hrs. (Class II). 	Step	Temp. (°C)	Time (min.)	1	Min. operating temp. +0/-3	30±3	2	Room temp.	2~3	3	Max. operating temp. +3/-0	30±3	4	Room temp.	2~3	<ul style="list-style-type: none"> No remarkable damage. Cap change : <ul style="list-style-type: none"> NP0: within ±2.5% or 0.25pF whichever is larger X7R, X5R: within ±7.5% Y5V: within ±20% * Q/D.F., I.R. and dielectric strength: To meet initial requirements.
Step	Temp. (°C)	Time (min.)																
1	Min. operating temp. +0/-3	30±3																
2	Room temp.	2~3																
3	Max. operating temp. +3/-0	30±3																
4	Room temp.	2~3																

No.	Item	Test Condition	Requirements																																																
13.	Humidity (Damp Heat) Steady State	<ul style="list-style-type: none"> * Test temp.: $40 \pm 2^\circ\text{C}$ * Humidity: 90~95% RH * Test time: $500 + 24/-0\text{hrs}$. * Measurement to be made after keeping at room temp. for 24 ± 2 hrs. (Class I) or 48 ± 4 hrs. (Class II). 	<ul style="list-style-type: none"> * No remarkable damage. * Cap change: NP0: within $\pm 5\%$ or $0.5\mu\text{F}$ whichever is larger X7R, X5R: $\geq 10\text{V}$, within $\pm 12.5\%$; 6.3V, within $\pm 25\%$ Y5V: $\geq 10\text{V}$, within $\pm 30\%$; 6.3V, within $+30/-40\%$ * Q/D.F. value: NP0: More than $30\mu\text{F}$ $Q \geq 350$, $10\mu\text{F} \leq C \leq 30\mu\text{F}$, $Q \geq 275 + 2.5C$ Less than $10\mu\text{F}$ $Q \geq 200 + 10C$ <p>X7R, X5R:</p> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th>Rated vol.</th> <th>D.F. \leq</th> <th>Exception of D.F. \leq</th> </tr> </thead> <tbody> <tr> <td>$\geq 50\text{V}$</td> <td>3%</td> <td>6% $0603 \geq 0.047\mu\text{F}; 0805 \geq 0.18\mu\text{F}; 1206 \geq 0.47\mu\text{F}$</td> </tr> <tr> <td rowspan="3">25V</td> <td rowspan="3">5%</td> <td>10% $0805 \geq 1\mu\text{F}; 1210 \geq 10\mu\text{F}$</td> </tr> <tr> <td>14% $0603 \geq 0.33\mu\text{F}; 1206 \geq 4.7\mu\text{F}$</td> </tr> <tr> <td>15% $0402 \geq 0.10\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 6.8\mu\text{F}$</td> </tr> <tr> <td rowspan="3">16V</td> <td rowspan="3">5%</td> <td>10% $0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}$</td> </tr> <tr> <td>15% $0402 \geq 0.033\mu\text{F}; 0603 \geq 0.68\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$</td> </tr> <tr> <td>15% $0402 \geq 0.33\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$</td> </tr> <tr> <td rowspan="2">10V</td> <td rowspan="2">7.5%</td> <td>20% $0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}$</td> </tr> <tr> <td>15% $0402 \geq 2.2\mu\text{F}; 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}$</td> </tr> <tr> <td>6.3V</td> <td>15%</td> <td>30% $0402 \geq 2.2\mu\text{F}; 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}$</td> </tr> </tbody> </table> <p>Y5V:</p> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th>Rated vol.</th> <th>D.F. \leq</th> <th>Exception of D.F. \leq</th> </tr> </thead> <tbody> <tr> <td>$\geq 50\text{V}$</td> <td>7.5%</td> <td>10% $0603 \geq 0.1\mu\text{F}; 0805 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}$</td> </tr> <tr> <td>35V</td> <td>10%</td> <td>---</td> </tr> <tr> <td rowspan="3">25V</td> <td rowspan="3">7.5%</td> <td>10% $0402 \geq 0.047\mu\text{F}; 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.33\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 4.7\mu\text{F}$</td> </tr> <tr> <td>15% $0402 \geq 0.068\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$</td> </tr> <tr> <td>16V (C < 1.0 μF)</td> <td>10%</td> <td>12.5% $0402 \geq 0.068\mu\text{F}; 0603 \geq 0.68\mu\text{F}$ 20% $0402 \geq 0.22\mu\text{F}$</td> </tr> <tr> <td>16V (C $\geq 1.0\mu\text{F}$)</td> <td>12.5%</td> <td>20% $0603 \geq 2.2\mu\text{F}; 0805 \geq 3.3\mu\text{F}; 1206 \geq 10\mu\text{F}; 1210 \geq 22\mu\text{F}; 1812 \geq 47\mu\text{F}$</td> </tr> <tr> <td>10V</td> <td>20%</td> <td>30% $0402 \geq 0.47\mu\text{F}$</td> </tr> <tr> <td>6.3V</td> <td>30%</td> <td>---</td> </tr> </tbody> </table>	Rated vol.	D.F. \leq	Exception of D.F. \leq	$\geq 50\text{V}$	3%	6% $0603 \geq 0.047\mu\text{F}; 0805 \geq 0.18\mu\text{F}; 1206 \geq 0.47\mu\text{F}$	25V	5%	10% $0805 \geq 1\mu\text{F}; 1210 \geq 10\mu\text{F}$	14% $0603 \geq 0.33\mu\text{F}; 1206 \geq 4.7\mu\text{F}$	15% $0402 \geq 0.10\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 6.8\mu\text{F}$	16V	5%	10% $0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}$	15% $0402 \geq 0.033\mu\text{F}; 0603 \geq 0.68\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$	15% $0402 \geq 0.33\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$	10V	7.5%	20% $0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}$	15% $0402 \geq 2.2\mu\text{F}; 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}$	6.3V	15%	30% $0402 \geq 2.2\mu\text{F}; 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}$	Rated vol.	D.F. \leq	Exception of D.F. \leq	$\geq 50\text{V}$	7.5%	10% $0603 \geq 0.1\mu\text{F}; 0805 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}$	35V	10%	---	25V	7.5%	10% $0402 \geq 0.047\mu\text{F}; 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.33\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 4.7\mu\text{F}$	15% $0402 \geq 0.068\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$	16V (C < 1.0 μF)	10%	12.5% $0402 \geq 0.068\mu\text{F}; 0603 \geq 0.68\mu\text{F}$ 20% $0402 \geq 0.22\mu\text{F}$	16V (C $\geq 1.0\mu\text{F}$)	12.5%	20% $0603 \geq 2.2\mu\text{F}; 0805 \geq 3.3\mu\text{F}; 1206 \geq 10\mu\text{F}; 1210 \geq 22\mu\text{F}; 1812 \geq 47\mu\text{F}$	10V	20%	30% $0402 \geq 0.47\mu\text{F}$	6.3V	30%	---
Rated vol.	D.F. \leq	Exception of D.F. \leq																																																	
$\geq 50\text{V}$	3%	6% $0603 \geq 0.047\mu\text{F}; 0805 \geq 0.18\mu\text{F}; 1206 \geq 0.47\mu\text{F}$																																																	
25V	5%	10% $0805 \geq 1\mu\text{F}; 1210 \geq 10\mu\text{F}$																																																	
		14% $0603 \geq 0.33\mu\text{F}; 1206 \geq 4.7\mu\text{F}$																																																	
		15% $0402 \geq 0.10\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 6.8\mu\text{F}$																																																	
16V	5%	10% $0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}$																																																	
		15% $0402 \geq 0.033\mu\text{F}; 0603 \geq 0.68\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$																																																	
		15% $0402 \geq 0.33\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$																																																	
10V	7.5%	20% $0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}$																																																	
		15% $0402 \geq 2.2\mu\text{F}; 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}$																																																	
6.3V	15%	30% $0402 \geq 2.2\mu\text{F}; 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}$																																																	
Rated vol.	D.F. \leq	Exception of D.F. \leq																																																	
$\geq 50\text{V}$	7.5%	10% $0603 \geq 0.1\mu\text{F}; 0805 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}$																																																	
35V	10%	---																																																	
25V	7.5%	10% $0402 \geq 0.047\mu\text{F}; 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.33\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 4.7\mu\text{F}$																																																	
		15% $0402 \geq 0.068\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$																																																	
		16V (C < 1.0 μF)	10%	12.5% $0402 \geq 0.068\mu\text{F}; 0603 \geq 0.68\mu\text{F}$ 20% $0402 \geq 0.22\mu\text{F}$																																															
16V (C $\geq 1.0\mu\text{F}$)	12.5%	20% $0603 \geq 2.2\mu\text{F}; 0805 \geq 3.3\mu\text{F}; 1206 \geq 10\mu\text{F}; 1210 \geq 22\mu\text{F}; 1812 \geq 47\mu\text{F}$																																																	
10V	20%	30% $0402 \geq 0.47\mu\text{F}$																																																	
6.3V	30%	---																																																	

*I.R.: $\geq 10\text{V}$, $1\text{G}\Omega$ or $50\ \Omega\cdot\text{F}$ whichever is smaller.

Class II (X7R, X5R, Y5V)



Rated voltage	Insulation Resistance
100V: X7R	
16V: 0402 $\geq 0.22\mu\text{F}$	1 $\text{G}\Omega$ or $R_x C \geq 10\ \Omega\cdot\text{F}$ whichever is smaller.
10V: 0201 $\geq 47\text{nF}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$	
6.3V	

No	Item	Test Condition			Requirements					
14	Humidity (Damp Heat) Load	<ul style="list-style-type: none"> * Test temp.: $40 \pm 2^\circ\text{C}$ * Humidity: 90~95%RH * Test time: $500+24/-0$ hrs. * To apply voltage : rated voltage. * Measurement to be made after keeping at room temp. for 24 ± 2 hrs. (Class I) or 48 ± 4 hrs. (Class II). 			<ul style="list-style-type: none"> * No remarkable damage. Cap change: NP0: $\pm 7.5\%$ or $0.75\mu\text{F}$ whichever is larger. X7R, X5R: $\geq 10\text{V}$, within $\pm 12.5\%$; 6.3V, within $\pm 25\%$ Y5V: $\geq 10\text{V}$, within $\pm 30\%$; 6.3V, within $+30/-40\%$ Q/D.F. value: NP0: $C \geq 30\text{pF}, Q \geq 200$; $C < 30\text{pF}, Q \geq 100 + 10/3C$ X7R, X5R: 					
		Rated vol.	D.F. \leq	Exception of D.F. \leq						
		$\geq 50\text{V}$	3%	6%	$0603 \geq 0.047\mu\text{F}; 0805 \geq 0.18\mu\text{F}; 1206 \geq 0.47\mu\text{F}$					
		25V	5%	10%	$0805 \geq 1\mu\text{F}; 1210 \geq 10\mu\text{F}$					
				14%	$0603 \geq 0.33\mu\text{F}; 1206 \geq 4.7\mu\text{F}$					
				15%	$0402 \geq 0.10\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 6.8\mu\text{F}$					
		16V	5%	10%	$0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}$					
				15%	$0402 \geq 0.033\mu\text{F}; 0603 \geq 0.68\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$					
		10V	7.5%	15%	$0402 \geq 0.33\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$					
				20%	$0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}$					
		6.3V	15%	30%	$0402 \geq 2.2\mu\text{F}; 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}$					
		Y5V:								
		Rated vol.	D.F. \leq	Exception of D.F. \leq						
		$\geq 50\text{V}$	7.5%	10%	$0603 \geq 0.1\mu\text{F}; 0805 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}$					
		25V	7.5%	10%	$0402 \geq 0.047\mu\text{F}; 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.33\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 4.7\mu\text{F}$					
				15%	$0402 \geq 0.068\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$					
				12.5%	$0402 \geq 0.068\mu\text{F}; 0603 \geq 0.68\mu\text{F}$					
		16V (C < 1.0μF)	10%	20%	$0402 \geq 0.22\mu\text{F}$					
					$0603 \geq 2.2\mu\text{F}; 0805 \geq 3.3\mu\text{F}; 1206 \geq 10\mu\text{F}; 1210 \geq 22\mu\text{F}; 1812 \geq 47\mu\text{F}$					
		16V (C ≥ 1.0μF)	12.5%	20%	$0402 \geq 0.47\mu\text{F}$					
		10V	20%	30%	$0402 \geq 0.47\mu\text{F}$					
		6.3V	30%	---	$---$					
		*I.R.: $\geq 10\text{V}$, $500\text{M}\Omega$ or $25\ \Omega\cdot\text{F}$ whichever is smaller. Class II (X7R, X5R, Y5V)								
		Rated voltage			Insulation Resistance					
		100V: X7R			500MΩ or $R \times C \geq 5\ \Omega\cdot\text{F}$ whichever is smaller.					
		16V: 0402 ≥ 0.22μF								
		10V: 0201 ≥ 47nF; 0402 ≥ 0.47μF; 0603 ≥ 0.47μF ; 0805 ≥ 2.2μF; 1206 ≥ 4.7μF; 1210 ≥ 47μF								
		6.3V								


No	Item	Test Condition				Requirements																																																													
15.	High Temperature Load (Endurance)	Test temp. : NP0, X7R/X7E: $125 \pm 3^\circ\text{C}$ X5R, Y5V: $85 \pm 3^\circ\text{C}$ Test time: $1000+24/-0$ hrs. To apply voltage: (1) 6.3V or $C \geq 10\mu\text{F}$ or TT series: 150% of rated voltage. (2) $10\text{V} \leq U_r < 500\text{V}$: 200% of rated voltage. (3) 500V : 150% of rated voltage. (4) $U_r \geq 630\text{V}$: 120% of rated voltage. (5) 100% of rated voltage for below range.				* No remarkable damage. Cap change: NP0: $\pm 3.0\%$ or $\pm 0.3\mu\text{F}$ whichever is larger X7R, X5R: $\geq 10\text{V}$, within $\pm 12.5\%$; 6.3V , within $\pm 25\%$ Y5V: $\geq 10\text{V}$, within $\pm 30\%$; 6.3V , within $+30/-40\%$ Q/D.F. value: NP0: More than $30\mu\text{F}$, $Q \geq 350$ $10\mu\text{F} \leq C < 30\mu\text{F}$, $Q \geq 275+2.5\text{C}$ Less than $10\mu\text{F}$, $Q \geq 200+10\text{C}$ X7R, X5R:																																																													
		<table border="1"> <thead> <tr> <th>Size</th><th>Dielectric</th><th>Rated voltage</th><th>Capacitance range</th></tr> </thead> <tbody> <tr> <td>0201</td><td>X5R</td><td>6.3V,10V</td><td>$C \geq 0.1\mu\text{F}$</td></tr> <tr> <td>0402</td><td>X5R, Y5V</td><td>6.3V,10V</td><td>$C \geq 1.0\mu\text{F}$</td></tr> <tr> <td>0603</td><td>X5R Y5V</td><td>6.3V,10V</td><td>$C \geq 4.7\mu\text{F}$ $TT \geq 2.2\mu\text{F}$</td></tr> <tr> <td>0805</td><td>X5R Y5V</td><td>6.3V</td><td>$C \geq 22\mu\text{F}$ $TT \geq 10\mu\text{F}$</td></tr> <tr> <td>1206</td><td>X5R Y5V</td><td>6.3V</td><td>$C \geq 47\mu\text{F}$ $TT \geq 22\mu\text{F}$</td></tr> </tbody> </table>				Size	Dielectric	Rated voltage	Capacitance range	0201	X5R	6.3V,10V	$C \geq 0.1\mu\text{F}$	0402	X5R, Y5V	6.3V,10V	$C \geq 1.0\mu\text{F}$	0603	X5R Y5V	6.3V,10V	$C \geq 4.7\mu\text{F}$ $TT \geq 2.2\mu\text{F}$	0805	X5R Y5V	6.3V	$C \geq 22\mu\text{F}$ $TT \geq 10\mu\text{F}$	1206	X5R Y5V	6.3V	$C \geq 47\mu\text{F}$ $TT \geq 22\mu\text{F}$	<table border="1"> <thead> <tr> <th>Rated vol.</th><th>D.F. \leq</th><th>Exception of D.F. \leq</th></tr> </thead> <tbody> <tr> <td>$\geq 50\text{V}$</td><td>3%</td><td>6% $0603 \geq 0.047\mu\text{F}; 0805 \geq 0.18\mu\text{F}; 1206 \geq 0.47\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>10% $0805 \geq 1\mu\text{F}; 1210 \geq 10\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>14% $0603 \geq 0.33\mu\text{F}; 1206 \geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>15% $0402 \geq 0.10\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 6.8\mu\text{F}$</td></tr> <tr> <td>$25\text{V}$</td><td>5%</td><td>10% $0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>15% $0402 \geq 0.033\mu\text{F}; 0603 \geq 0.68\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$</td></tr> <tr> <td>$16\text{V}$</td><td>5%</td><td>10% $0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>15% $0402 \geq 0.033\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$</td></tr> <tr> <td>$10\text{V}$</td><td>7.5%</td><td>15% $0402 \geq 0.33\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>20% $0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}$</td></tr> <tr> <td>$6.3\text{V}$</td><td>15%</td><td>30% $0402 \geq 2.2\mu\text{F}; 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}$</td></tr> </tbody> </table>		Rated vol.	D.F. \leq	Exception of D.F. \leq	$\geq 50\text{V}$	3%	6% $0603 \geq 0.047\mu\text{F}; 0805 \geq 0.18\mu\text{F}; 1206 \geq 0.47\mu\text{F}$			10% $0805 \geq 1\mu\text{F}; 1210 \geq 10\mu\text{F}$			14% $0603 \geq 0.33\mu\text{F}; 1206 \geq 4.7\mu\text{F}$			15% $0402 \geq 0.10\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 6.8\mu\text{F}$	25V	5%	10% $0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}$			15% $0402 \geq 0.033\mu\text{F}; 0603 \geq 0.68\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$	16V	5%	10% $0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}$			15% $0402 \geq 0.033\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$	10V	7.5%	15% $0402 \geq 0.33\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$			20% $0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}$	6.3V	15%	30% $0402 \geq 2.2\mu\text{F}; 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}$
Size	Dielectric	Rated voltage	Capacitance range																																																																
0201	X5R	6.3V,10V	$C \geq 0.1\mu\text{F}$																																																																
0402	X5R, Y5V	6.3V,10V	$C \geq 1.0\mu\text{F}$																																																																
0603	X5R Y5V	6.3V,10V	$C \geq 4.7\mu\text{F}$ $TT \geq 2.2\mu\text{F}$																																																																
0805	X5R Y5V	6.3V	$C \geq 22\mu\text{F}$ $TT \geq 10\mu\text{F}$																																																																
1206	X5R Y5V	6.3V	$C \geq 47\mu\text{F}$ $TT \geq 22\mu\text{F}$																																																																
Rated vol.	D.F. \leq	Exception of D.F. \leq																																																																	
$\geq 50\text{V}$	3%	6% $0603 \geq 0.047\mu\text{F}; 0805 \geq 0.18\mu\text{F}; 1206 \geq 0.47\mu\text{F}$																																																																	
		10% $0805 \geq 1\mu\text{F}; 1210 \geq 10\mu\text{F}$																																																																	
		14% $0603 \geq 0.33\mu\text{F}; 1206 \geq 4.7\mu\text{F}$																																																																	
		15% $0402 \geq 0.10\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 6.8\mu\text{F}$																																																																	
25V	5%	10% $0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}$																																																																	
		15% $0402 \geq 0.033\mu\text{F}; 0603 \geq 0.68\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$																																																																	
16V	5%	10% $0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}$																																																																	
		15% $0402 \geq 0.033\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$																																																																	
10V	7.5%	15% $0402 \geq 0.33\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$																																																																	
		20% $0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}$																																																																	
6.3V	15%	30% $0402 \geq 2.2\mu\text{F}; 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}$																																																																	
		(6) 150% of rated voltage for below range. <table border="1"> <thead> <tr> <th>Size</th><th>Dielectric</th><th>Rated voltage</th><th>Capacitance range</th></tr> </thead> <tbody> <tr> <td>0402</td><td>X5R</td><td>10V,16V</td><td>$C \geq 0.22\mu\text{F}$</td></tr> <tr> <td></td><td>Y5V</td><td>16V</td><td>$C \geq 0.47\mu\text{F}$</td></tr> <tr> <td>0603</td><td>X5R</td><td>10V,16V</td><td>$C \geq 1.0\mu\text{F}$</td></tr> <tr> <td></td><td>Y5V</td><td>16V</td><td>$C \geq 2.2\mu\text{F}$</td></tr> <tr> <td>0805</td><td>X5R</td><td>10V</td><td>$C \geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td>Y5V</td><td>16V</td><td>$C \geq 4.7\mu\text{F}$</td></tr> </tbody> </table>				Size	Dielectric	Rated voltage	Capacitance range	0402	X5R	10V,16V	$C \geq 0.22\mu\text{F}$		Y5V	16V	$C \geq 0.47\mu\text{F}$	0603	X5R	10V,16V	$C \geq 1.0\mu\text{F}$		Y5V	16V	$C \geq 2.2\mu\text{F}$	0805	X5R	10V	$C \geq 4.7\mu\text{F}$		Y5V	16V	$C \geq 4.7\mu\text{F}$	Y5V: <table border="1"> <thead> <tr> <th>Rated vol.</th><th>D.F. \leq</th><th>Exception of D.F. \leq</th></tr> </thead> <tbody> <tr> <td>$\geq 50\text{V}$</td><td>7.5%</td><td>10% $0603 \geq 0.1\mu\text{F}; 0805 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}$</td></tr> <tr> <td>35V</td><td>10%</td><td>---</td></tr> <tr> <td>25V</td><td>7.5%</td><td>10% $0402 \geq 0.047\mu\text{F}; 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.33\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 4.7\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>15% $0402 \geq 0.068\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$</td></tr> <tr> <td>$16\text{V}$ ($C < 1.0\mu\text{F}$)</td><td>10%</td><td>12.5% $0402 \geq 0.068\mu\text{F}; 0603 \geq 0.68\mu\text{F}$</td></tr> <tr> <td></td><td></td><td>20% $0402 \geq 0.22\mu\text{F}$</td></tr> <tr> <td>$16\text{V}$ ($C \geq 1.0\mu\text{F}$)</td><td>12.5%</td><td>20% $0603 \geq 2.2\mu\text{F}; 0805 \geq 3.3\mu\text{F}; 1206 \geq 10\mu\text{F}; 1210 \geq 22\mu\text{F}; 1812 \geq 47\mu\text{F}$</td></tr> <tr> <td>10V</td><td>20%</td><td>30% $0402 \geq 0.47\mu\text{F}$</td></tr> <tr> <td>$6.3\text{V}$</td><td>30%</td><td>---</td></tr> </tbody> </table>		Rated vol.	D.F. \leq	Exception of D.F. \leq	$\geq 50\text{V}$	7.5%	10% $0603 \geq 0.1\mu\text{F}; 0805 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}$	35V	10%	---	25V	7.5%	10% $0402 \geq 0.047\mu\text{F}; 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.33\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 4.7\mu\text{F}$			15% $0402 \geq 0.068\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$	16V ($C < 1.0\mu\text{F}$)	10%	12.5% $0402 \geq 0.068\mu\text{F}; 0603 \geq 0.68\mu\text{F}$			20% $0402 \geq 0.22\mu\text{F}$	16V ($C \geq 1.0\mu\text{F}$)	12.5%	20% $0603 \geq 2.2\mu\text{F}; 0805 \geq 3.3\mu\text{F}; 1206 \geq 10\mu\text{F}; 1210 \geq 22\mu\text{F}; 1812 \geq 47\mu\text{F}$	10V	20%	30% $0402 \geq 0.47\mu\text{F}$	6.3V	30%	---		
Size	Dielectric	Rated voltage	Capacitance range																																																																
0402	X5R	10V,16V	$C \geq 0.22\mu\text{F}$																																																																
	Y5V	16V	$C \geq 0.47\mu\text{F}$																																																																
0603	X5R	10V,16V	$C \geq 1.0\mu\text{F}$																																																																
	Y5V	16V	$C \geq 2.2\mu\text{F}$																																																																
0805	X5R	10V	$C \geq 4.7\mu\text{F}$																																																																
	Y5V	16V	$C \geq 4.7\mu\text{F}$																																																																
Rated vol.	D.F. \leq	Exception of D.F. \leq																																																																	
$\geq 50\text{V}$	7.5%	10% $0603 \geq 0.1\mu\text{F}; 0805 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}$																																																																	
35V	10%	---																																																																	
25V	7.5%	10% $0402 \geq 0.047\mu\text{F}; 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.33\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 4.7\mu\text{F}$																																																																	
		15% $0402 \geq 0.068\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$																																																																	
16V ($C < 1.0\mu\text{F}$)	10%	12.5% $0402 \geq 0.068\mu\text{F}; 0603 \geq 0.68\mu\text{F}$																																																																	
		20% $0402 \geq 0.22\mu\text{F}$																																																																	
16V ($C \geq 1.0\mu\text{F}$)	12.5%	20% $0603 \geq 2.2\mu\text{F}; 0805 \geq 3.3\mu\text{F}; 1206 \geq 10\mu\text{F}; 1210 \geq 22\mu\text{F}; 1812 \geq 47\mu\text{F}$																																																																	
10V	20%	30% $0402 \geq 0.47\mu\text{F}$																																																																	
6.3V	30%	---																																																																	
		* Measurement to be made after keeping at room temp. for 24 ± 2 hrs. (Class I) or 48 ± 4 hrs. (Class II).				* I.R.: $\geq 10\text{V}, 1\text{G}\Omega$ or $50 \Omega\text{-F}$ whichever is smaller. Class II (X7R, X5R, Y5V)																																																													
						<table border="1"> <thead> <tr> <th>Rated voltage</th><th>Insulation Resistance</th></tr> </thead> <tbody> <tr> <td>100V: X7R</td><td rowspan="4">$1\text{G}\Omega$ or $R \times C \geq 10 \Omega\text{-F}$ whichever is smaller.</td></tr> <tr> <td>16V: 0402 $\geq 0.22\mu\text{F}$</td></tr> <tr> <td>10V: 0201 $\geq 47\mu\text{F}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$</td></tr> <tr> <td>6.3V</td></tr> </tbody> </table>			Rated voltage	Insulation Resistance	100V: X7R	$1\text{G}\Omega$ or $R \times C \geq 10 \Omega\text{-F}$ whichever is smaller.	16V: 0402 $\geq 0.22\mu\text{F}$	10V: 0201 $\geq 47\mu\text{F}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$	6.3V																																																				
Rated voltage	Insulation Resistance																																																																		
100V: X7R	$1\text{G}\Omega$ or $R \times C \geq 10 \Omega\text{-F}$ whichever is smaller.																																																																		
16V: 0402 $\geq 0.22\mu\text{F}$																																																																			
10V: 0201 $\geq 47\mu\text{F}$; 0402 $\geq 0.47\mu\text{F}$; 0603 $\geq 0.47\mu\text{F}$; 0805 $\geq 2.2\mu\text{F}$; 1206 $\geq 4.7\mu\text{F}$; 1210 $\geq 47\mu\text{F}$																																																																			
6.3V																																																																			

APPENDIXES

□ Tape & reel dimensions




Size	0402	0603	0805			1206			1210		1812
Thickness	N	S, X	A	B	C, D, I	B	C, J, D	G	C, D, G	M	D, K
A₀	0.62±0.05	1.02±0.05	1.50±0.10	1.50±0.10	<1.57	2.00±0.10	<1.85	<1.95	<2.97	<2.97	<3.81
B₀	1.12±0.05	1.80±0.05	2.30±0.10	2.30±0.10	<2.40	3.50±0.10	<3.46	<3.67	<3.73	<3.73	<5.30
T	0.60±0.05	0.95±0.05	0.75±0.05	0.95±0.05	0.23±0.05	0.95±0.05	0.23±0.05	0.23±0.05	0.23±0.05	0.23±0.05	0.25±0.05
K₀	-	-	-	-	<2.50	-	<2.50	<2.50	<2.50	<3.00	<2.50
W	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	12.0±0.20
P₀	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.100	4.00±0.10	4.00±0.10
10xP₀	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10	40.0±0.10
P₁	2.00±0.05	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	8.00±0.10
P₂	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D₀	1.55±0.05	1.55±0.05	1.55±0.05	1.55±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05	1.50±0.05
D₁	-	-	-	-	1.00±0.10	-	1.00±0.10	1.00±0.10	1.00±0.10	1.00±0.10	1.50±0.10
E	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10
F	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	5.50±0.05



Size	0402, 0603, 0805, 1206, 1210			1812
Reel size	7"	10"	13"	7"
C	13.0+0.5/-0.2	13.0+0.5/-0.2	13.0+0.5/-0.2	13.0+0.5/-0.2
W₁	8.4+1.5/-0	8.4+1.5/-0	8.4+1.5/-0	12.4+2.0/-0
A	178.0±0.10	250.0±1.0	330.0±1.0	178.0±0.10
N	60.0+1.0/-0	100.0±1.0	100±1.0	60.0+1.0/-0

□ Description of customer label



- a. Customer name
- b. WTC order series and item number
- c. Customer P/O
- d. Customer P/N
- e. Description of product
- f. Quantity
- g. Bar code including quantity & WTC P/N or customer
- h. WTC P/N
- i. Shipping date
- j. Order bar code including series and item numbers
- k. Serial number of label

□ Constructions

No.	Name	NP0*	NPO, X7R, Y5V
①	Ceramic material	BaTiO ₃ based	
②	Inner electrode	AgPd alloy	Ni
③	Termination	Inner layer	Ag
④		Middle layer	Ni
⑤		Outer layer	Sn




Fig. 5 The construction of MLCC

* Partial NPO items are with Ag/Ni/Sn terminations, please ref to product range of NPO dielectric for detail.

□ Storage and handling conditions

- (1) To store products at 5 to 40°C ambient temperature and 20 to 70%. related humidity conditions.
- (2) The product is recommended to be used within one year after shipment. Check solderability in case of shelf life extension is needed.

Cautions:

- a. Don't store products in a corrosive environment such as sulfide, chloride gas, or acid. It may cause oxidization of electrode, which easily be resulted in poor soldering.
- b. To store products on the shelf and avoid exposure to moisture.
- c. Don't expose products to excessive shock, vibration, direct sunlight and so on.

□ Recommended soldering conditions

The lead-free termination MLCCs are not only to be used on SMT against lead-free solder paste, but also suitable against lead-containing solder paste. If the optimized solder joint is requested, increasing soldering time, temperature and concentration of N₂ within oven are recommended.




Fig. 6 Recommended reflow soldering profile for SMT process with SnAgCu series solder paste.




Fig. 7 Recommended wave soldering profile for SMT process with SnAgCu series solder.